



CC14K Grout

CEMENTITIOUS HIGH STRENGTH WIND TURBINE GROUT

ITEM NUMBER CC 14K GROUT

DESCRIPTION

CC 14K GROUT is a hydraulic-cement based, precision, non-shrink, load-bearing grout having an extended working time up to 30 minutes under fluid condition. CC 14K GROUT is designed to transfer load effectively and safely, ensuring long service time of the grouted item. It is a non-corrosive, non-metallic, mineral-based precision grout, developed to have a high initial and ultimate flexural and compressive strength. It can be mixed quickly, as needed, on the jobsite. CC 14K GROUT offers exceptional workability and is easily placed by pouring or pumping. The product is designed to give non-shrink performance under various conditions for both interior and exterior applications.

INDUSTRY USES

- Machinery and equipment base plates / wind turbines / generators / rolling mills / compressors
- Soleplates / bridge seats / precast columns
- Beams / steel column pads / precast beams
- Anchoring guardrails / sign posts / anchor bolts / guide wires / dowels

BENEFITS AND FEATURES

- May be mixed to plastic, flowable, and fluid consistencies for easy application.
- Very high compressive and flexural strengths
- High modulus to ensure proper load transfer
- Non-shrink ensures proper load transfer
- Quickly and easily placed by pouring or pumping
- Resists heat up to 600°F (315°C)
- Resists many chemicals, including oils, petroleum products, solvents and mild caustic alkalis
- May be extended up to 50%
- No added chloride or gypsum
- Outstanding flow characteristics; maintains flow for up to 30 minutes at fluid consistency.

TECHNICAL DATA

C191 Set Time	Initial Set Final Set	Plastic	Fluid
		15 minutes 28 minutes	57 minutes 80 minutes
C109 Compressive Strength	1 day 7 days 28 days	Plastic	Fluid
		8,800 psi (MPa 60.7)	7,200 psi (MPa 49.6)
		10,900psi (MPa 75.1)	8,200 psi (MPa 56.5)
		12,300 psi (MPa 84.8)	10,700 psi (MPa 73.8)

PACKAGING

50lb Bag

Yield – approx. 0.44 ft³/bag at high flow

Shelf Life: 12 months properly stored

Storage Conditions: Store in unopened container in a dry and cool area

SURFACE PREPARATION

All grout contact surfaces must be free of oil, grease, scale, penetrating sealers or all other types of contaminants that will interfere with the bond. Mechanically roughen or high pressure water-jet the existing concrete substrate. Surface must be rough in profile, but generally level. Grouting area must be saturated with water 12-24 hours prior to grouting. Remove all excess water before placing grout.

Form preparation: Forming method must provide for rapid, continuous grout placement. For pouring, allow a minimum clearance of 3" for entry and 6" minimum grout "head". Forming must also provide venting to avoid entrapment of air. Provide ½" minimum form clearance on all sides and 1" clearance for head. Ensure form is well sealed and an appropriate form release agent has been applied for that type of form.



CC14K Grout

MIXING

Small quantities of CC 14K GROUT may be hand-mixed in a concrete mixing pan until lump-free. For large quantities and continuous pours, mix using a mortar mixer with rubber tipped blades or appropriate grout pump for a minimum of 3 minutes or until lump-free and uniform consistency. Use the minimum water required to produce desired placement consistency.

- Use 3.8 quarts (3.7L) of water per bag for plastic consistency
- Use 4.0 quarts (3.875L) of water for medium flow (pourable)
- Use 4.3 quarts (4.0L) of water for high flow

Mix in 2 steps

1. Add 2/3 of water requirement then add grout
2. After partial mixing, add remainder of water for desired consistency. Thoroughly mix total quantity for 2-3 minutes.

Do not mix more than can be placed in 15 minutes at 75° F (24° C). Do not re-temper.

PLACEMENT

CC 14K GROUT is easily placed by pouring or pumping and compaction can be accomplished by rodding or tapping. Place grout on one side, flowing to opposite and adjacent side, to avoid entrapment of air. When necessary provide vent holes. Grout head and excess grout may be removed after initial set.

CAUTION

Safety Considerations

- Use of safety goggles and chemical resistant gloves are recommended
- Use of NIOSH/MSHA/OSHA approved respirator is recommended if ventilation is inadequate
- Avoid breathing vapors
- Avoid skin contact

First Aid

- **EYE CONTACT:** Flush immediately with water for at least 15 minutes. Contact physician immediately.
- **RESPIRATORY CONTACT:** Remove person to fresh air.
- **SKIN CONTACT:** Remove any contaminated clothing.

KEEP CONTAINER TIGHTLY CLOSED – KEEP OUT OF REACH OF CHILDREN – NOT FOR INTERNAL CONSUMPTION – FOR INDUSTRIAL USE ONLY

LIMITED WARRANTY

All information provided by Cornerstone Construction Material LLC (CCM) concerning CCM products, including but not limited to, any recommendations and advice relating to the application and use of CCM products, is given in good faith based on CCM's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with CCM's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of CCM's control are such that CCM assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the CCM product(s) must test the product(s) for suitability for the intended application and purpose before proceeding the full application of the product(s). CCM reserves the right to change the properties of its products without notice. All sales of CCM product(s) are subject to its current terms and conditions of sale.

Prior to each use of any CCM product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Safety Data Sheet which are available at www.ccmaterial.com. Nothing contained in any CCM materials relieves the user of the obligation to read and follow the warnings and instruction for each CCM product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use.

CCM warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet when used in accordance with the written instructions. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CCM SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL



Cornerstone
Construction
Material, LLC

CC14K Grout

DAMAGES. CCM SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.